

Metal Roof and Wall Panel Components in Contact with Preservative-Treated Lumber

Background

Developments during the past several years in the preservative-treated lumber industry have led to the introduction of both metal-free preservatives as well as treatments utilizing dispersed or micronized copper metal. Several of these new products allow much broader contact with other metal sheathing and connectors without the use of a barrier material. These newer treatments can even allow the use of aluminum products without a barrier.

Historically, preservative-treated lumber was treated with copper-containing chemistry which was corrosive toward both certain types of metal roof or wall panels and most recommended fasteners. The process of corrosion is relatively simple. The copper-containing chemistry in the lumber reacts through a catalyst, typically water, with the dissimilar metal panel or fastener resulting in galvanic corrosion.

The Metal Construction Association suggests that copper-containing preservative-treated lumber should ideally be separated from metal roof or wall panels and accessory materials using a polymeric membrane material between the metal panel and the wood substrate. While newer non-metallic and micronized copper preservatives may allow direct contact with metal roofing, it is important to check with the preservative manufacturer for their recommendations regarding contact and fasteners. In many installations, the choice of compatible metal fasteners is critical to the integrity of the metal roof or wall assembly. The exception to this would be where the metal panels or fasteners are constructed of copper or copper alloys.

Discussion

Wood preservatives and treatments have been used for decades to prevent damage by termites and other insects, decay from fungi, and damage from fire. One of the more popular treatments was Chromated Copper Arsenate (CCA), invented in 1933 and not widely used in residential construction until the late 1960s. At that time, the other primary preservatives in use were creosote, a coal/tar derivative, and pentachlorophenol (penta), an oil-based preservative.

CCA gained popularity over creosote and penta because it was cleaner and easier to work with. However in 2003, the EPA and the treating industry announced it would phase out the use of CCA for residential and consumer applications as a precaution due to health concerns. In response, the American Wood Protection Association (AWPA) announced a voluntary change to the formulations of wood preservatives. Lumber treated with CCA is still used for building poles, timber columns, saltwater exposure, utility poles, pilings, and guard rail posts. However, it is no longer used for decking and most applications involving dimension lumber.

With the voluntary withdrawal of CCA from the marketplace, the wood preservative industry responded by offering an assortment of treatments that included Alkaline Copper Quaternary (ACQ), Copper Azole (CA) and Ammoniacal Copper Zinc Arsenate (ACZA). A new generation of micronized copper products and certain metal free preservatives has also been introduced and are some of the significant products used in the market today. These chemical treatments contain biocides that do not include arsenic or chromium, and are currently acceptable to the EPA.

The preservative treated lumber, where copper is the main ingredient of the preservative, performed similarly to CCA treated lumber. However, it was soon discovered these preservatives also can be corrosive toward metal, other than copper or copper alloys, in situations where the lumber will be exposed to moisture.

Corrosivity of Preservative-Treated Lumber

Corrosion of metals in an aqueous environment is an electrochemical process involving two steps:

- 1) Water and oxygen, must diffuse to the metal surface, and
- 2) Reactants must have enough energy to complete the reaction.

Within preservative-treated lumber, some of the preservative chemicals bond to the wood and a small percentage remain in ionic form. The ionic components increase the corrosiveness of the wood product toward metal. At higher moisture contents, wood conducts electricity and ions better, and therefore, the corrosion reaction occurs at a faster rate. It is believed that corrosion activity within wood requires moisture content of 20% or greater.⁽¹⁾

New preservative formulations such as ACQ, CA, and MCQ contain much more copper than CCA. Copper ions can accelerate the corrosion of steel and aluminum.

The potential for corrosion of hardware in contact with treated wood occurs when metals in the preservative (such as copper) are different from the metals in the hardware (the iron in steel, or aluminum). In a wet environment these dissimilar metals create a small electrical current that triggers a chemical reaction resulting in galvanic corrosion. This is the challenge in selecting proper fasteners and connectors to be used with preservative treated wood. The MCA's Technical Bulletin on Fastener Selection Guideline addresses this for metal panels as follows:⁽²⁾

“ACQ or CA preservative-treated lumber can be incompatible with certain types of fasteners. In those cases where any type of metal roof or wall cladding materials are being attached to preservative-treated lumber, the following fasteners are not compatible: zinc plated screws, zinc-alloy headed screws, stainless capped screws, aluminum, copper and copper alloy.

Metal panel fasteners that are compatible with preservative-treated lumber are stainless steel fasteners, or hot dip galvanized nails manufactured to ASTM A153 class D or heavier. Other types of fasteners coated with proprietary anti-corrosive technologies may be compatible for use with preservative-treated lumber. Allowable use should be verified with the fastener manufacturer.”

Industry Positions

The manufacturers of wood preservative chemicals make specific recommendations regarding unpainted galvanized or Galvalume sheet panels. Generally they advise against direct, long-term contact with wood treated with the newer copper based preservatives such as ACQ, CA, or MCQ. Both the International Building Code and the International Residential Code require that stainless steel or hot-dipped galvanized fasteners meeting ASTM International A153 *Standard Specification for Zinc coating (Hot-Dip) on Iron and Steel Hardware* be used. Connectors must be ASTM A653, *Standard Specification for Steel Sheet, Zinc-coated (Galvanized) or Zinc-Iron Alloy-coated (Galvannealed) by the Hot-Dip Process*, Class G185 sheet or better for protection against the effects of moisture where treated wood is used.

The manufacturers also recommend that aluminum not be used in direct contact with preservative-treated lumber that is not treated using metal-free or micronized copper preservatives. In these cases, MCA suggests that metal materials, other than copper or copper alloys, should be separated from the treated lumber with a physical barrier that prevents contact with the metal panels or chemicals leaching through to the metal panels such as, but not

limited to, rubber, vinyl, plastic sheeting, asphalt roofing paper, or a maintained industrial coating.⁽³⁾

Specific Steel Industry Recommendations

Wheeling Corrugating:

Wheeling Corrugating^(a) conducted a study to determine the effectiveness of a specific barrier in preventing the corrosive attack between treated lumber and metal wall panels.⁽⁴⁾ The research was conducted by H.L. Stauver of Touchstone Research Laboratory, Ltd, in Triadelphia, W. VA. The conclusion from that study was:

“Water and ice shield material was most effective in preventing a corrosive reaction between any of the steel products tested and either type (ACQ and copper azole) of pressure-treated lumber. Effectively, there was no surface damage where the water/ice shield contacted the metal or painted surfaces. The use of 30-pound roofing felt was somewhat effective in minimizing the corrosion of the various steel products, but does not appear to offer substantial improvement over direct metal to wood contact. Direct contact with the pressure-treated lumber grades had the anticipated effect of corrosion on both the galvanized products and two of the painted steel materials in that the paint and the base steel were damaged by direct contact with the treated lumber...it is recommended that all galvanized be protected with water/ice shield membrane or with a similar product in any construction.”

^(a) Wheeling Corrugating is no longer involved in the manufacture of roof sheathing materials.

U.S. Steel:

U. S. Steel tested preservative-treated lumber in contact with their architectural sheet steel products commonly used for metal roofing and siding applications. Products included G90, Galvalume, acrylic-coated Galvalume, prepainted HDG, and

prepainted Galvalume. The preservative-treated lumber included CCA and ACQ chemicals. The results showed that ACQ was generally more corrosive to most coated steel products.

U.S. Steel concluded that isolating steel from preservative-treated lumber using water resistant barrier materials is an effective way to minimize corrosion. The isolating products would include peel-and-stick polymeric membranes, polymer tapes, masking and lining materials. They also concluded that using isolating materials with a paper or felt component should be avoided since they can retain moisture which can increase corrosion potential.⁽⁵⁾

National Frame Building Association (NFBA):

Most metal component manufacturers recommend that panels or flashing should not come into contact with preservative-treated lumber. Many manufacturers recommend installing a barrier material that will stop all electrical current between the treated lumber and metal. Furthermore, NFBA suggests that water should not drain off of treated lumber onto panels or flashing.⁽⁶⁾

National Roofing Contractors Association (NRCA):

The NRCA recognizes the lack of long-term corrosion performance data on newer preservative-treated lumber such as ACQ, CA, MCQ in contact with metal fasteners, panels and flashing. Their guidelines include the following:

- *“Aluminum fasteners, flashings and accessory products should not be used in direct contact with any treated wood. ACQ-treated wood is not compatible with aluminum.*
- *Uncoated metal and painted metal flashings and accessories, except for 300-series stainless steel, should not be used in direct contact with treated wood. Metal products, except stainless steel, may be used if separated from treated wood by a spacer or barrier, such as single-ply*

membrane or self-adhered polymer-modified bitumen membrane material.”⁽⁷⁾

NRCA also states ... “NRCA is of the opinion that the corrosion-related concerns regarding the use of currently available treated wood possibly outweigh the benefits that treated wood provides as a component in roof assemblies. In many instances, non-treated, construction- grade wood is suitable for use in roof assemblies as blocking or nailers, provided reasonable measures are taken to ensure the nontreated wood remains reasonably dry when in service. Where a specific construction detail provides for a secondary means of waterproofing, NRCA now considers the use of nontreated, construction-grade wood to be an acceptable substitute for treated wood.”⁽⁷⁾

Steel Deck Institute:

The SDI conducted tests of G60, G90, and primed steel deck in contact with ACQ and Copper Azole preservative-treated lumber. They also evaluated the performance with a barrier between the pressure (preservative) treated lumber and the steel specimens. The barriers were 30 pound felt paper and water/ice shield. Using the AWWA procedure E12 “Standard Method for Determining Corrosion of Metal in Contact with Treated Wood”, the SDI found the following:

“The results of this study found that the use of water and ice shield material was most effective in preventing a corrosive reaction between any of the steel products tested and either type of pressure treated lumber. Effectively, there was no surface damage where the water/ice shield contacted the metal or painted surfaces. The use of 30 pound roofing felt was somewhat effective in minimizing the corrosion of the various steel products, but does not appear to offer substantial improvement over direct metal to wood contact. Direct contact with the pressure treated lumber grades had the anticipated effect of corrosion on both the galvanized products and the painted steel materials

in that the zinc coating and/or the paint and the base steel were damage by direct contact with the treated lumber.”⁽⁸⁾

As a result, the Steel Deck Institute recommends a barrier of water-and-ice shield or equivalent be used between pressure treated lumber and steel deck products or accessories.

Summary

Based on the information and testing experience gathered from a variety of sources, it is clear that the use of any of the commercially available copper-containing preservative-treated lumber in direct contact with certain metal products could lead to accelerated corrosion and affect the long-term integrity and performance of a metal roof or wall system. The most effective way to avoid corrosion is to ensure that the treated lumber used is either manufactured using the newer metal-free preservatives, micronized copper treatment or that there is a separation between the metal roof or wall panel and the pressure (preservative) treated wood with some type of barrier material. (The preservative-treated lumber manufacturer should always be contacted to verify that the material may be used in contact with the intended metal components.)

The Metal Construction Association suggests that, unless specifically treated with metal-free preservatives or some of the newer technologies, copper-containing preservative-treated lumber should be separated from metal roof or wall panels and accessory materials by a barrier membrane material between the metal panel and the wood substrate. In those installations, the choice of compatible metal fasteners is also critical to the integrity of the metal roof or wall assembly.

The Metal Construction Association will continue to monitor the recommendations from the wood

preservative industry before and inform the market as further developments are made and validated.

References

- (1) Flynn, K., Quarles, S., and Shelly, JI, Non-Biological Deterioration of Wood, Forest Products Laboratory, University of California, 1995.
- (2) *Fastener Selection Guideline*, Metal Construction Association Technical Bulletin, May 2008.
- (3) H. DeVenzio, Treated Wood, *The Construction Specifier*, May 2005.
- (4) Tests Shed Light on Corrosion, *Rural Builder*, May 2005.
- (5) *ACQ Pressure Treated Lumber Effect on Sheet Steel*, United States Steel Corporation Technical Bulletin, TBP 2005.19.
- (6) *Pressure-Treated Wood for Post-Frame Construction*, published by the National Frame Building Association.
- (7) *The NRCA Roofing Manual: Architectural Metal Flashing, Condensation and Air Leakage Control, and Reroofing* published by the National Roofing Contractors Association, 2014.
- (8) *Steel Deck Products in Contact with Pressure Treated Lumber*, Steel Deck Institute Position Statement, August 2006.

Founded in 1983, the Metal Construction Association brings together the diverse metal construction industry for the purpose of expanding the use of all metals used in construction. MCA promotes the benefits of metal in construction through:

- Technical guidance
- Product certification
- Educational and awareness programs
- Advocating for the interests of our industry
- Recognition of industry-achievement awards

- Monitoring of industry issues, such as codes and standards
- Research to develop improved metal construction products
- Promotional and marketing support for the metal construction industry
- Publications to promote use of metal wall and roof products in construction

For more information, please visit the MCA Web site at www.metalconstruction.org

Copyright © 2014 Metal Construction Association. All rights reserved.

No part of this publication may be reproduced in any form or by any means, including photocopying, or utilized by any information storage or retrieval system without permission of the copyright owner.

This bulletin is for general information only. The bulletin is designed to delineate areas requiring consideration. Information contained in the bulletin should not be used without first securing competent advice with respect to its suitability for any given application. MCA does not assume responsibility and disclaims any representation or warranty, express or implied, that such information is suitable for any general or particular use. Anyone making use of the bulletin assumes all liability resulting from such use.

The existence of the bulletin does not in any respect preclude a member or nonmember of MCA from manufacturing, selling, or specifying products not conforming to the bulletin, nor does the existence of an MCA bulletin preclude its voluntary use by persons other than MCA members. The bulletin does not purport to address all safety problems associated with its use or all applicable regulatory requirements. It is the responsibility of the user of the guideline to establish appropriate safety and health practices and to determine the applicability of regulatory limitations before use of the bulletin.

© 6/2014

METAL CONSTRUCTION ASSOCIATION

8735 W. Higgins Road, Suite 300, Chicago, IL 60631

847.375.4718 | mca@metalconstruction.org | www.metalconstruction.org

BUILD LEGACIES
 METAL

The Metal Construction Association reserves the right to change, revise, add to, or delete any data contained in the bulletin without prior notice. It is the responsibility of the end user to verify the applicability of this information with the local building and fire officials.

© 6/2014

METAL CONSTRUCTION ASSOCIATION

8735 W. Higgins Road, Suite 300, Chicago, IL 60631

847.375.4718 | mca@metalconstruction.org | www.metalconstruction.org

BUILD LEGACIES
 **METAL**